MicroCoat Technologies

1316 Somerset Drive McKinney, TX 75070 www.m-coat.com Tel +1-972-678-4950 Fax +1-214-257-8890



Unparalleled in Polymer Coatings and Adhesives Technology

PRODUCT DATA SPECIFICATION

MCT SD0802G/5JS

A High Performance

Single Component, Very High Thermal Conductivity, Very Low Resistivity Conductive Epoxy Interposer for Connecting Silicon Stacked Die Lavers

MicroCoat Technologies announces the arrival of their new It is 100% solids, and posses' good handling and storage (tested to date) with a 7 day room temperature working life. range -55°C - 225°C; Short term to 300°C. Besides the cost and space savings compared to

wirebonding the conductive paths provide a ground-breaking method for helping to cool the device(s) with the high thermal conductivity of the epoxy acting as cooling fins. It is shown that a 32MB 3D stacked DRAM cache can reduce the cycles per memory access of a twothreaded RMS benchmark on average by 13% and as much as 55% while increasing the peak temperature by a negligible 0.08°C. Offdie BW and power are also reduced by 66% on average. It is also shown that a 3D floorplan of a high performance microprocessor can simultaneously reduce power 15% and increase performance 15% with a small 14°C increase in peak temperature. Voltage scaling can reach neutral thermals with a simultaneous 34% power reduction and 8% performance improvement. Bryan Black, et al, Intel Corporation.

This adhesive is a thixotropic silver filled conductive frozen adhesive capable of dispensed line widths of 50 microns.

low resistivity - high thermal conductivity die-stacking properties. This silver-filled conductive adhesive is designed interconnect conductive adhesive MCT SD0802C. Many to bond from IC to IC on Silicon with either gold or aluminum companies that are manufacturing stacked flash devices pads. It also bonds ICs and components to advanced have gone to very fine line dispensed conductive adhesive substrates such as ceramic, PBGAs, CSPs and array instead of wirebonding to make the connections from layer packages with virtually no bleed. Hydrophobic and stable at to layer. MCT has developed a magnificent solution. It can high temperatures, the adhesive produces a void-free line be a dispensed bead or using high speed jet dispensing of with excellent interfacial adhesion strength. This material is conductive adhesive, the material can be applied at 50 formulated to provide high cohesive energy, adhesive microns wide with no sag or slump to 16+ flash layers strength, and elongation at break. Operating temperature



Middle

Stop

Composition Properties

Filler Contents: Viscositv: Thixotropic Thixo Ratio at above viscosity parameters Average Particle Size:

Typical Cured Properties

Volume Resistivity: **Thermal Conductivity** CTE Alpha 1 ppm/°C CTE Alpha 2 ppm/°C Tg°C Die Shear psi Shore "D" Hardness Post Cure Ionics 883/5011.3.8.7 85+% Silver 20-35 Kcps @ 10 RPM Brookfield HBT CP51. ~1.89 - 2.30 .70 - 1.25 microns

Start

.00015 - .00008mohms (Dispensed) 11.0 - 11.9W/m-K 50 200 117 >8000 75 - 80 Cl=<6ppm, Na+=<3.3ppm, K+=<1.1ppm Teflon Flask 5 gm sample using 20-40 mesh, 50 gm DI H₂O, 100°C for 24 hours

Modulus:

@65C = 5595 MPa, @25C = 5510 MPa, @150C = 925 MPa, @250C = 310 MPa

<u>Processing Procedures:</u> Mixing: The material should be lightly stirred prior to use if used from a jar. Not required if in a syringe

Application: The material may be applied by Jet Spray, screen printing or syringe dispense

Curing: Cure at 150°C for 45 minutes. Optimum conditions will vary depending upon application and will need to be determined experimentally.

Storage MicroCoat should be stored in sealed containers away from heat or flames. It has a shelf life of 7-9 days at a storage temperature of 25°C, 3 months at -10°C or 6 months at -40°C. **DO NOT STORE AT TEMPERATURE BELOW** -40°C. Material **may** be returned to refrigerator/freezer after using partial syringes or jars if within the shelf life window.

 $\label{eq:packaging: sc, and 10cc syringes Shipped in Freeze Packs next day delivery only v.R.022712$

The information contained herein, is, to the best of our knowledge accurate. However, MicroCoat Technology does not assume any liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any material is the sole responsibility of the user. The information contained herein is considered typical properties and is not intended to be used as specifications for our products. This information is offered solely to assist purchasers in selecting the appropriate products for purchaser's own testing. All products may present unknown hazards and should be used with the proper precautions. Although certain hazards are described herein and in the Material Safety Data Sheets, we cannot guarantee that these are the only hazards that exist. Repeated and prolonged exposure to epoxy resins can cause sensitization or other allergic responses.